

# Santoprene™ 201-64

## Thermoplastic Vulcanizate

Product Description		Key Features	
<p>A soft, colorable, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable.</p>		<ul style="list-style-type: none"> <li>UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component.</li> <li>Although not NSF certified, this product has a Material Supplier Form on file with NSF to facilitate its evaluation for use in applications requiring NSF certification.</li> <li>Recommended for applications requiring excellent flex fatigue resistance.</li> <li>Excellent ozone resistance.</li> <li>RoHS compliant.</li> </ul>	

  

General			
Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>Europe</li> <li>Latin America</li> </ul>	<ul style="list-style-type: none"> <li>North America</li> <li>South America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>Automotive - Plugs, Bumpers, Grommets, Clips</li> <li>Automotive - Seals and Gaskets</li> </ul>	<ul style="list-style-type: none"> <li>Industrial - Seals and Gaskets</li> <li>Soft Touch Grips</li> </ul>	<ul style="list-style-type: none"> <li>Tubing</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Appliance Components</li> <li>Automotive Applications</li> <li>Automotive Interior Trim</li> <li>Automotive Under the Hood</li> </ul>	<ul style="list-style-type: none"> <li>Consumer Applications</li> <li>Diaphragms</li> <li>Electrical Parts</li> <li>Gaskets</li> </ul>	<ul style="list-style-type: none"> <li>Seals</li> <li>Tubing</li> </ul>
Agency Ratings	<ul style="list-style-type: none"> <li>EU Annex XVII of Regulation (EC) No 1907/2006</li> </ul>	<ul style="list-style-type: none"> <li>UL QMFZ2</li> </ul>	<ul style="list-style-type: none"> <li>UL QMFZ8</li> </ul>
RoHS Compliance	<ul style="list-style-type: none"> <li>RoHS Compliant</li> </ul>		
Automotive Specifications	<ul style="list-style-type: none"> <li>CHRYSLER MS-AR100 BGN</li> <li>FORD WSD-M2D379-A1</li> </ul>	<ul style="list-style-type: none"> <li>GM GMP.E/P.002</li> <li>GM GMW15813, Type 5</li> </ul>	
UL File Number	<ul style="list-style-type: none"> <li>E80017</li> </ul>		
Color	<ul style="list-style-type: none"> <li>Natural Color</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>Blow Molding</li> <li>Coextrusion</li> <li>Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>Extrusion Blow Molding</li> <li>Injection Blow Molding</li> <li>Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>Multi Injection Molding</li> <li>Profile Extrusion</li> <li>Sheet Extrusion</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>01/22/2013</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Specific Gravity	0.970	0.970	ASTM D792
Density	0.970 g/cm <sup>3</sup>	0.970 g/cm <sup>3</sup>	ISO 1183
Detergent Resistance	f3	f3	UL 749
Detergent Resistance	f4	f4	UL 2157

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness	Shore A, 15 sec, 73°F (23°C), 0.0787 in (2.00 mm)	69	ISO 868

Typical properties: these are not to be construed as specifications.

©2013 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

**ExxonMobil Chemical Santoprene™ 201-64**
**Thermoplastic Vulcanizate**

<b>Elastomers</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	450 %	450 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	450 %	450 %	ISO 37
Tear Strength - Across Flow (73°F (23°C), Die C)	131 lbf/in	23.0 kN/m	ASTM D624
Tear Strength - Across Flow 73°F (23°C), Method Bb, Angle (Nicked)	130 lbf/in	23 kN/m	ISO 34-1
Compression Set			ASTM D395B
158°F (70°C), 22.0 hr, Type 1	18 %	18 %	
257°F (125°C), 70.0 hr, Type 1	44 %	44 %	
Compression Set			ISO 815
158°F (70°C), 22.0 hr, Type A	18 %	18 %	
257°F (125°C), 70.0 hr, Type A	44 %	44 %	
<b>Thermal</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Brittleness Temperature	-76 °F	-60 °C	ASTM D746
Brittleness Temperature	-76 °F	-60 °C	ISO 812
RTI Elec	212 °F	100 °C	UL 746
RTI Str			UL 746
0.0394 in (1.00 mm)	194 °F	90.0 °C	
0.0591 in (1.50 mm)	194 °F	90.0 °C	
0.118 in (3.00 mm)	203 °F	95.0 °C	
<b>Electrical</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	<b>Test Based On</b>
Dielectric Strength			ASTM D149
73°F (23°C), 0.0800 in (2.03 mm)	750 V/mil	30 kV/mm	
Dielectric Constant			ASTM D150
73°F (23°C), 0.0780 in (1.98 mm)	2.30	2.30	
Dielectric Constant			IEC 60250
73°F (23°C), 0.0780 in (1.98 mm)	2.30	2.30	
Comparative Tracking Index (CTI)	PLC 0	PLC 0	UL 746
High Amp Arc Ignition (HAI)	PLC 0	PLC 0	UL 746
High Voltage Arc Resistance to Ignition (HVAR)	PLC 6	PLC 6	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 1	PLC 1	UL 746
Hot-wire Ignition (HWI)	PLC 2	PLC 2	UL 746
<b>Injection</b>	<b>Typical Value (English)</b>	<b>Typical Value (SI)</b>	
Drying Temperature	180 °F	82.2 °C	
Drying Time	3.0 hr	3.0 hr	

Typical properties: these are not to be construed as specifications.

©2013 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

# ExxonMobil Chemical Santoprene™ 201-64

## Thermoplastic Vulcanizate

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Moisture	0.080 %	0.080 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	350 °F	177 °C
Middle Temperature	360 °F	182 °C
Front Temperature	360 °F	182 °C
Nozzle Temperature	370 to 430 °F	188 to 221 °C
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C
Mold Temperature	50.0 to 125 °F	10.0 to 51.7 °C
Injection Rate	Fast	Fast
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	100 to 200 rpm	100 to 200 rpm
Clamp Tonnage	3.0 to 5.0 tons/in <sup>2</sup>	41 to 69 MPa
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	16.0:1.0 to 20.0:1.0
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0
Vent Depth	0.0010 in	0.025 mm

### Injection Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

Extrusion	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82.2 °C
Drying Time	3.0 hr	3.0 hr
Melt Temperature	385 °F	196 °C
Die Temperature	390 °F	199 °C
Back Pressure	725 to 2900 psi	5.00 to 20.0 MPa

### Extrusion Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Extrusion Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ASTM D573
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ISO 188
Change in Ultimate Elongation in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ASTM D573
Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ISO 188
Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ASTM D573
Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ISO 188
Continuous Upper Temperature Resistance 1008 hr	275 °F	135 °C	SAE J2236

Typical properties: these are not to be construed as specifications.

©2013 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

# ExxonMobil Chemical Santoprene™ 201-64

## Thermoplastic Vulcanizate

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Flammability	Typical Value (English)	Typical Value (SI)	Test Based On
Flame Rating			UL 94
0.0394 in (1.00 mm)	HB	HB	
0.0591 in (1.50 mm)	HB	HB	
0.118 in (3.00 mm)	HB	HB	

### Additional Information

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080").

Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.

Compression set at 25% deflection.

### Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

### Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Material Safety Data Sheet, Injection Molding Guide and Extrusion Guide.

### Notes

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas	Asia Pacific	Europe, Middle East and Africa
ExxonMobil Chemical Company 13501 Katy Freeway Houston, TX 77079-1398 USA 1-281-870-6050	ExxonMobil Chemical Asia Pacific 1 HarbourFront Place #06-00 HarbourFront Tower One Singapore 098633 +65-2-1638699	ExxonMobil Chemical Europe Hermeslaan 2 1831 Machelen, Belgium 420-239-016-274

Typical properties: these are not to be construed as specifications.

©2013 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.